

Chemical	Rating	Chemical	Rating
Ethylene Glycol	A	Octane	A
Ethylene Oxide	A	Oleic Acid	A
F Fatty Acids	B	Ozone	A
Ferric Chloride	A	P Perchloric Acid	D
Formaldehyde	B	Phenol	C/D
Formic Acid	A	Phosphoric Acid (Up to 30%)	A
G Gasoline	D	Potassium Borate	A
Glucose	A	Potassium Bromide	A
Glycol	A	Potassium Hydroxide	A
Glycolic Acid	A	Potassium Nitrate	A
H Heptane	D	Propane	D
Hexane	D	S Salt/Sea Water	A
Hydrochloric Acid (Up to 30%)	A	Silicic Acid	A
Hydrofluoric Acid (Up to 75%)	A	Silicone Oils/Greases	C/D
Hydrogen	A	Silver Nitrate	A
Hydrogen Peroxide (Up to 20%)	A	Soap Solutions	A
I Iso Octane	C	Sodium Bicarbonate	A
Isopropyl Ether	B	Sodium Chloride	A
K Kerosene	C	Sodium Hydroxide (Up to 70%)	A
L Lactic Acid	A	Sodium Nitrate (General)	A
Lead Acetate	A	Sodium Phosphate	A
Linseed Oil	B	Stannous Chloride (Up to 15%)	A
Lubricating Oils	C	Stearic Acid	A
M Magnesium Chloride	A	Styrene	C
Magnesium Hydroxide	A	Sulfur	A
Magnesium Salts	A	Sulfuric Acid (Up to 60%)	A
Magnesium Sulfate	A	Sulfurous Acid	A
Mercuric Chloride	A	T Tartaric Acid	A
Mercury	A	Toluene	D
Methyl Amine	B	Turpentine	D
Methyl Bromide	D	U Urea	A
Methyl Chloride	D	V Vinegar	A
Methyl Ethyl Ketone	B	W Water	A
Methylene Chloride	D	X Xylene	D
Mineral Oils	C/D	Z Zinc Chloride	A
N Naptha	C	Zinc Salts	A
Naphthalene	C/D	Zinc Sulphate	A
Nitric Acid (Up to 25%)	A		

Rating Code: A = Excellent, B = Good, C = Fair, D = Not Recommended

Please be aware that this information is for guidance only and the ratings have been derived from a correlation of available data. Performance in service can be affected by many different factors and actual grade of Dryflex® XL, suitability must be determined by user evaluation under actual service conditions. The VTC TPE Group assumes no liability for the accuracy or completeness of the given information. Please contact a VTC TPE Group representative for any additional information required.