

mediprene[®] of

OIL



OIL-FREE COMPOUNDS

TTPPE



Mediprene® OF series

Oil Free grades for medical applications

Pure and Safe

The Mediprene® oil free compounds were developed to address demands for transparent medical thermoplastic elastomer (TPE) grades with a minimum of potential extractables and leachables.

The compounds, called Mediprene® OF series, prevent the possibility of oil migrating or leaching out of the material, a key requirement for medical and healthcare-related devices. They are ideal for sensitive medical applications where transparency is also required.

Special features

- Minimum of potential extractables and leachables
- PVC, silicone and latex free
- Soft-touch appeal
- 40 to 90 Shore A
- Transparent
- Production site accredited to ISO 13485
- Sterilizable with gamma, ethylene oxide (EtO) and steam
- Flexibility over broad temperature range
- Excellent sealing and adhesion

Easy flowing grades

We have developed several grades with a higher melt flow rate. This makes them more easy-flowing for injection moulding thinner wall parts, such as thin-wall patches or connectors.

Regulatory compliance

Representative Mediprene® grades have passed cytotoxicity tests according to ISO 10993-5 and are compliant with USP Class VI.

Mediprene® TPE materials are PVC, silicone and latex free, making them allergen free and a viable alternative to PVC based compounds.

Applications

Hot melt adhesives (for example for connections) adhere well to the Mediprene® OF series. These compounds also show excellent performance with double-coated tapes for "stick to skin" applications such as patches for fixation of tubing or other medical components to skin.

A selection of Mediprene® Oil Free grades

Material	Hardness Shore A	Colour	Specific Gravity g/cm ³	Tensile Strength MPa	Elongation at Break %	Tear Strength kN/mm	Modulus 100% MPa	Modulus 300% MPa	MFR 5 kg/190°C g/10 min
Test Method	ASTM D 2240 ¹		ASTM D 792	ASTM D 638	ASTM D 638	ASTM D 624	ASTM D 638	ASTM D 638	ASTM D 1238
OF 400M	40	Transparent	0.89	7	700	14	0.8	1.3	2
OF 500M	50	Transparent	0.89	10	700	20	1.1	1.9	2
OF 600M	60	Transparent	0.89	9	600	30	1.6	2.8	2
OF 700M	70	Transparent	0.89	11	600	41	2.5	4.0	2
OF 800M	80	Transparent	0.89	13	600	58	4.5	6.4	2
OF 900M	90	Transparent	0.89	18	600	69	5.8	7.5	2
OF 601M	60	Transparent	0.89	14	650	40	1.4	3.1	9
OF 701M	70	Transparent	0.89	15	650	46	2.4	4.6	10
OF 801M	80	Transparent	0.89	15	650	55	3.7	5.9	11
OF 901M	90	Transparent	0.89	15	650	63	5.0	7.1	12

¹⁾ 4mm

Processing

The material has excellent processing characteristics and can be processed using conventional thermoplastic fabricating methods, including injection moulding and extrusion.

Processing Temperatures

Barrel Temperatures °C

Mould Temperatures °C

Injection Moulding

180 - 230

20 - 50

Extrusion

150 - 210

Service Temperature Range:

-50 to +80°C (for 40 and 50 Sh A OF, unstressed material)

-50 to +125°C (for 60 – 90 Sh A OF, unstressed material)

Presentation:

Free flowing pellets that can be processed without predrying, when stored under normal conditions.

The above information is, to the best of our knowledge, true and accurate, but any recommendations or suggestions which may be made are without guarantee, since the conditions of use are beyond our control. which may be made are without guarantee, since the conditions of use are beyond our control.

Vita Thermoplastic Polymers (VTP) and VTC Elastoteknik AB are members of the VTC TPE Group

Vita Thermoplastic Polymers (VTP)

United Kingdom

t : 44 (0)161 654 6616

f : 44 (0)161 654 2333

sales@vtctpe.com

VTC Elastoteknik AB

Sweden

t : 46 (0) 532 60 75 00

f : 46 (0) 532 60 75 99

info@elastoteknik.se

Paris Office

France

t : 33 (0) 160 43 17 17

f : 33 (0) 160 43 11 13

pgruyer@aol.com

For further information or to download this and other publications please visit

www.mediprene.com



www.mediprene.com